



ACROLON® PUR COLOR PLUS

ACRYLIC POLYURETHANE DIRECT TO METAL COATING

Revised 07/2023 Issue 1

PRODUCT DESCRIPTION

A 2-pack acrylic polyurethane zinc phosphate topcoat with a matt finish

- 1-coat system directly on steel and galvanized steel
- Wide range of dry film thicknesses per coat from 60- 160 µm
- UV- and weather resistant
- Tough-elastic and solid, non-brittle

RECOMMENDED USE

Can be used as a topcoat for the application direct on steel and hot-dip galvanized steel.

Also recommended as a topcoat in conjunction with Zinc Clad®, Dura Plate® or Macropoxy® high performance primers and intermediate coats.

PRODUCT TECHNICAL DATA

Volume Solids:	65 ± 2% (ISO 3233-3)
Weight Solids:	75 ± 2%
VOC:	300 g/l determined practically in accordance with Protective Coatings Directive of German Paint Industry Association (VdL-RL 04). 317 g/l calculated from formulation to satisfy EC Solvent Emissions Directive. 265 g/kg calculated from formulation to satisfy EC Solvent Emissions Directive (UK).
Colours:	Wide range of RAL- and NCS colour shades available. Slight colour deviations are possible due to raw material characteristics.
Flash Point:	Base: 31°C, Hardener: 38°C.
Cleaner/Thinner:	Thinner EG (for cleaning). Thinner EG for thinning with max. 3% to adapt the viscosity. Thinning will affect VOC compliance, sag tolerance and dry film thicknesses.
Pack Size:	A two component material supplied in separate containers to be mixed prior to use: 30 kg (25 litre) unit when mixed. Volume will vary with colours and density.
Mixing Ratio:	92 parts base to 8 parts hardener by weight 10.5 parts base to 1 part hardener by volume* *Note: The mixing ratio by volume varies depending on the colour shade. If in doubt, please contact Sherwin-Williams. We recommend only mixing complete units. When part mixing, please use the mixing ratio by weight. Sherwin-Williams cannot be held responsible for mixing errors.
Density:	1.2 kg/l (may vary with colours).
Shelf Life:	2 years from date of manufacture, stored in originally sealed containers in a cool and dry environment.

Recommended Application Methods:

Airless Spray, Brush and Roller

Typical Thickness:

	Recommended Spreading Rate Per Coat		Maximum Sag
	Typical		
Dry	80 µm	160 µm	400 µm
Wet	123 µm	246 µm	615 µm
Theoretical Consumption*	0.148 kg/m ² 0.123 l/m ²	0.295 kg/m ² 0.246 l/m ²	
Theoretical Coverage*	6.77 m ² /kg 8.13 m ² /l	3.39 m ² /kg 4.06 m ² /l	

* This figure makes no allowance for surface profile, uneven application, overspray or losses in containers and equipment.

Film thickness will vary depending on actual use and specification.

Pot Life:

+ 10°C	+ 20°C	+ 30°C
4 hours	2 hours	1 hours

Pot life is dependent on temperature and volume.



ACROLON® PUR COLOR PLUS

ACRYLIC POLYURETHANE DIRECT TO METAL COATING

Revised 07/2023 Issue 1

AVERAGE DRYING TIMES

For 80 µm Dry Film Thickness:

	+ 5°C	+ 10°C	+ 20°C	+ 40°C
Dry to handle (Drying Stage 6*)	16 hours	6 hours	3 hours	1 hour
To Recoat	16 hours	6 hours	3 hours	1 hour

For 160 µm Dry Film Thickness:

	+ 5°C	+ 10°C	+ 20°C	+ 40°C
Dry to handle (Drying Stage 6*)	20 hours	10 hours	5 hours	1.5 hours
To Recoat	20 hours	10 hours	5 hours	1.5 hours

*ISO 9117

Maximum recoat time is unlimited. Prior to further applications possible contamination must be removed.

Final cure: 1-2 weeks, depending on film thickness and temperature. These figures are given as a guide only. Factors such as air movement, film thickness and humidity must also be considered.

APPROVALS & ENDORSEMENTS

Certificates according to ISO 12944-6, corrosivity categories C2 high and C3 high are available.

SURFACE PREPARATION

Ensure surfaces to be coated are clean, dry and free from all surface contamination such as oil, grease, dirt and corrosion products to achieve satisfactory adhesion.

For contaminated and weathered surfaces e.g. primed areas we recommend to clean with Cleaner Wash.

Steel surfaces shall be blast-cleaned to Sa 2½ according to ISO 8501-1 (ISO 12944-4).

Hot-dip galvanized surfaces shall be prepared by sweep blasting according to ISO 12944-4 with a non-ferrous blasting abrasive.

MIXING

Stir component A very thoroughly using a mechanical paint mixer (start slowly, then increase up to approx. 300 rpm). Add component B carefully and mix both components very thoroughly (including sides and bottom of the container). Mix for at least 3 minutes until a homogeneous mixture is achieved. We recommend to fill the mixed material into a clean container and mix again shortly as described above to avoid incorrect mixing. During mixing and handling of the materials always wear protective goggles, suitable gloves and other protective clothing.

APPLICATION CONDITIONS

Substrate temperature shall be above + 5°C and at least 3°C above the dew point.

Material temperature shall be above + 5°C.

Relative air humidity shall be below 85%.

APPLICATION EQUIPMENT

The following is a guide. Changes in pressures and tip sizes may be needed for satisfactory application characteristics. Always purge spray equipment before use with listed cleaner. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.

Airless Spray

Unit: Efficient airless equipment

Tip Size: 0.38 – 0.53 mm (0.015 – 0.021 inch)

Fan Angle: 40° - 80°

Operating Pressure: min. 180 bar (2600 psi)

The airless spray details given above are intended as a guide only.

Details such as fluid hose length and diameter, paint temperature and job shape and size all have an effect on the spray tip and operating pressure chosen. However, the operating pressure should be the lowest possible consistent satisfactory atomisation.

As conditions will vary from job to job, it is the applicators responsibility to ensure that the equipment in use has been set up to give the best results.

If in doubt consult Sherwin-Williams customer service.

Brush and Roller

The coating is suitable for brush and roller application. Application of more than one coat may be necessary to give equivalent dry film thickness to a single spray applied coat.



ACROLON® PUR COLOR PLUS

ACRYLIC POLYURETHANE DIRECT TO METAL COATING

Revised 07/2023 Issue 1

RECOMMENDED SYSTEMS

Steel

1 x Acrolon® PUR Color Plus

Also compatible with a wide range of Sherwin-Williams Macropoxy®, Dura-Plate® and Zinc Clad® epoxy primers and intermediate coats.

Hot-dip galvanized steel

1 x Acrolon® PUR Color Plus.

Certain shades for example, yellows and reds may require additional coats to achieve full opacity.

ADDITIONAL NOTES

Drying times, curing times and pot life should be considered as a guide only.

Chemical resistance:

Resistant to weathering, increased humidity and short term exposure to de-icing salts, acid and alkali vapours, oils, grease and short-term exposure to fuels and solvents.

Temperature resistance:

Dry heat up to + 150°C, short term up to + 200°C.

In case of higher temperatures consult Sherwin-Williams customer service.

An exposure to high temperatures can lead to colour changes.

Numerical values quoted for physical data may vary slightly from batch to batch.

HEALTH & SAFETY

Consult Product Health and Safety Data Sheet for information on safe storage, handling and application of this product.

WARRANTY

Whilst all statements made about our products (whether in this data sheet or otherwise) are correct and accurate to the best of our knowledge, we have no control over the quality or the condition of the substrate, the application conditions or the many other factors affecting your use and application of our product.

The appropriateness of the product under the actual conditions of application or intended use must be determined exclusively by you. The content of this document, and of any oral or written statements already made or to be made in relation to the subject matter of this document, including any suggestions as to appropriate products and any proposed application methods, technical details and other product information represent only test results or experience obtained under controlled or defined circumstances, and is therefore provided for general information purposes only.

Unless we agree specifically in writing to do so, we will not be liable to you for any loss or damage whether in contract, tort (including negligence), breach of statutory duty, misrepresentation, misstatement or otherwise, arising under or in connection with this document or such statements.

We disclaim any express or implied representations, warranties or guarantees (including any implied warranty of merchantability or fitness for a particular purpose), though nothing in this disclaimer excludes or limits our liability for death or personal injury arising from our negligence, or our fraud or fraudulent misrepresentation, or any other liability that cannot be excluded or limited by law.

All products supplied and technical advice given are subject to our Standard Terms and Conditions of Sale which you should request a copy of and review carefully.

This document may be modified and updated from time to time, and is uncontrolled once printed. It is the users responsibility to ensure they are using the most up to date version – this can be found at: www.sherwin-williams.com/protectiveEMEA.

If this datasheet has been translated, then it has been done using the English version as the source. In case of any queries, please refer to the master English version which can be found at: www.sherwin-williams.com/protectiveEMEA.