

## **Protective & Marine Coatings**PRODUCT DATA SHEET

### **CLEANER WASH**

# ALKALINE SURFACTANT SOLUTION FOR SURFACE CLEANING

Revised 07/2023 Issue 1

#### PRODUCT DESCRIPTION

A highly efficient, surface-active, aqueous cleaning agent. This alkaline cleaning agent is solvent free and biodegradable (in accordance with OECD guideline).

- · Suitable for dirty and weathered surfaces of all types
- · Emulsifies and dissolves persisting contaminates

#### **RECOMMENDED USE**

Can be used as an intensive cleaner of metallic (e.g. galvanised, aluminium) or coated surfaces which have been contaminated with water insoluble, oily, greasy substances or which have been exposed to weather

If non-visible contaminants are suspected we recommend to carry out tests according to DIN/TR 55684:2021-01.

Not suitable for removal of adhered cement and concrete deposits or corrosion products.

#### PRODUCT TECHNICAL DATA

#### Colours:

Colourless

Flash Point:

Cleaner: >101°C

#### Pack Size:

Cleaner concentrate supplied in PE canister: 5 litre

#### Mixing Ratio:

For use diluted with water to a ratio of 1:20 up to a maximum of 1:5 (Cleaner:Water).

#### Theoretical:

Approx. 100 - 150 g/m² in low-pressure spray process (dilution ratio 1:5)

Approx. 200 - 300 g/m2 in high-pressure spray process

(dilution ratio 1:20)

The consumption depends on several factors and may differ from the theoretical values.

#### Density:

1.05 kg/l

#### Shelf Life:

Unlimited, stored in originally sealed canisters in a cool and dry environment.



## **Protective & Marine Coatings**PRODUCT DATA SHEET

### **CLEANER WASH**

## ALKALINE SURFACTANT SOLUTION FOR SURFACE CLEANING

Revised 07/2023 Issue 1

#### **APPLICATION EQUIPMENT**

#### Application is carried out in three steps

- Remove heavily dirt and contaminants from surface with high-pressure hot water cleaning (water temperature approx. + 80°C, pressure 150 bar (2200 psi)).
- 2. Spray on diluted Cleaner Wash and leave to work for about 10 minutes. If it dries prematurely (sun, wind), respray.
- 3. Rinse off with high-pressure hot water cleaning (water temperature approx. + 80°C, pressure 150 bar (2200 psi)).

The cleaned surface must be absolutely dry before coating.

#### High-pressure spraying process

- Cleaner Wash is either added undiluted to the cleaning agent tank of the high pressure cleaner (note the adding options, dilution ratio may between 1:20 and 1:5) or is pumped diluted directly out of a supply container.
- During spraying, the pressure must be reduced to the equipment minimum of 20 30 bar (290 340 psi)
- Use a flat or variable nozzle (minimum spray angle 40°, reduce nozzle size to equipment-specific minimum)
- If cleaning agent feed rate is too high, use variable high pressure equipment correspondingly

#### Low-pressure spray process

- Alternatively a pump spray device can be used (e.g. 10 litre sprayer, 6 bar overpressure)
- Fill with Cleaner Wash diluted to ratio of 1:5 (Cleaner:Water).

#### **HEALTH & SAFETY**

Consult Product Health and Safety Data Sheet for information on safe storage, handling and application of this product.

#### **WARRANTY**

Whilst all statements made about our products (whether in this data sheet or otherwise) are correct and accurate to the best of our knowledge, we have no control over the quality or the condition of the substrate, the application conditions or the many other factors affecting your use and application of our product.

The appropriateness of the product under the actual conditions of application or intended use must be determined exclusively by you. The content of this document, and of any oral or written statements already made or to be made in relation to the subject matter of this document, including any suggestions as to appropriate products and any proposed application methods, technical details and other product information represent only test results or experience obtained under controlled or defined circumstances, and is therefore provided for general information purposes only.

Unless we agree specifically in writing to do so, we will not be liable to you for any loss or damage whether in contract, tort (including negligence), breach of statutory duty, misrepresentation, misstatement or otherwise, arising under or in connection with this document or such statements.

We disclaim any express or implied representations, warranties or guarantees (including any implied warranty of merchantability or fitness for a particular purpose), though nothing in this disclaimer excludes or limits our liability for death or personal injury arising from our negligence, or our fraud or fraudulent misrepresentation, or any other liability that cannot be excluded or limited by law.

All products supplied and technical advice given are subject to our Standard Terms and Conditions of Sale which you should request a copy of and review carefully.

This document may be modified and updated from time to time, and is uncontrolled once printed. It is the users responsibility to ensure they are using the most up to date version – this can be found at: <a href="https://www.sherwin-williams.com/protectiveEMEA">www.sherwin-williams.com/protectiveEMEA</a>.

If this datasheet has been translated, then it has been done using the English version as the source. In case of any queries, please refer to the master English version which can be found at: <a href="https://www.sherwin-williams.com/protectiveEMEA">www.sherwin-williams.com/protectiveEMEA</a>.