



KEM-KROMIK™ 6630 HIGH SOLID / EG

1-PACK SYNTHETIC RESIN COAT

Revised 09/2023 Issue 2

PRODUCT DESCRIPTION

A surface tolerant oxidative drying high build alkyd coating pigmented with zinc phosphate.
Low solvent content according to Protective Coatings Directive of German Paint Industry Association (VdL-RL 04).

- Excellent corrosion protection even in chemically aggressive atmosphere
- Excellent adhesion to steel, hot-dip galvanized surfaces, stainless steel, copper, aluminium, hard PVC and timber
- No brittleness due to an unique binder combination

RECOMMENDED USE

Can be used as a weather resistant, high build topcoat on steel and hot-dip galvanized surfaces in rural, industrial and marine atmosphere e.g. pipelines, bridges, metal facades, roofs, lattice masts, street lights, wall- and ceiling cladding, outside protection of silos.
Also suitable for the application on stainless steel, copper, aluminium, hard PVC and timber.
Not suitable for windows and doors.

PRODUCT TECHNICAL DATA

Volume Solids: 61 ± 2% (MIO), 62 ± 2% (MIO-free) (ISO 3233-3)

Weight Solids: 77 ± 2% (MIO), 77 ± 2% (MIO-free)

VOC: 322 g/l (345 g/l MIO shades) determined practically in accordance with Protective Coatings Directive of German Paint Industry Association (VdL-RL 04).
330 g/l (353 g/l MIO shades) calculated from formulation to satisfy EC Solvent Emissions Directive.
236 g/kg (236 g/kg MIO shades) calculated from formulation to satisfy EC Solvent Emissions Directive (UK).

Colours: Kem-Kromik™ 6630 High Solid EG: MIO-colour shades.
Kem-Kromik™ 6630 High Solid: RAL-colour shades.
In case of very intensive colour shades the colour pigments may be rubbed out of the surface.
Therefore it's not recommended for use on hand rails and other building components in public areas.
Slight colour deviations are possible due to raw material characteristics.
In case of strong UV exposure brilliant colour shades tend to fade.

Flash Point: 40°C.

Cleaner/Thinner: Thinner B (for cleaning).
Thinner B for thinning with max. 3% to adapt the viscosity.
Thinning will affect VOC compliance, sag tolerance and dry film thicknesses.

Pack Size: Single component material:
Kem-Kromik™ 6630 High Solid EG (MIO): 15 kg (10 litre).
Kem-Kromik™ 6630 High Solid: 30 kg (21.4 litre) and 15 kg (10.7 litre).
Volume will vary with colours and density.

Density: 1.5 kg/l (MIO)
1.4 kg/l (RAL)
(may vary with colours).

Shelf Life: 2 years from date of manufacture, stored in originally sealed containers in a cool and dry environment.

Recommended Application Methods:
Airless Spray, Conventional Spray, Brush and Roller

Typical Thickness:

Recommended Spreading Rate Per Coat		
MIO-shades	Typical	Maximum Sag
Dry	80 µm	240 µm
Wet	131 µm	393 µm
Theoretical Consumption*	0.197 kg/m ² 0.131 l/m ²	
Theoretical Coverage*	5.08 m ² /kg 7.63 m ² /l	
RAL-shades	Typical	Maximum Sag
Dry	80 µm	240 µm
Wet	129 µm	387 µm
Theoretical Consumption*	0.181 kg/m ² 0.129 l/m ²	
Theoretical Coverage*	5.54 m ² /kg 7.75 m ² /l	

* This figure makes no allowance for surface profile, uneven application, overspray or losses in containers and equipment.

Film thickness will vary depending on actual use and specification.

Apart from small areas the dry film thickness of Kem-Kromik™ 6630 High Solid / EG should not exceed 240 µm per coat.



KEM-KROMIK™ 6630 HIGH SOLID / EG

1-PACK SYNTHETIC RESIN COAT

Revised 09/2023 Issue 2

AVERAGE DRYING TIMES

For 80 µm Dry Film Thickness:

	+ 20°C
Dust-dry	4-5 hours
Dry to touch	8-10 hours
To Recoat	24 hours

Maximum recoat time is 6 months. Prior to further applications all contamination must be removed. In the case of extended recoating times consult Sherwin Williams customer service.

Final cure: 1 week, depending on film thickness and temperature.

These figures are given as a guide only. Factors such as air movement, film thickness and humidity must also be considered.

SURFACE PREPARATION

Ensure surfaces to be coated are clean, dry and free from all surface contamination such as oil, grease, dirt and corrosion products to achieve satisfactory adhesion.

For contaminated and weathered surfaces e.g. primed areas we recommend to clean with Cleaner Wash.

Steel surfaces shall be blast-cleaned to Sa 2½ according to ISO 8501-1 (ISO 12944-4)

Hot-dip galvanized surfaces, stainless steel, copper, aluminium and hard PVC shall be prepared by degreasing.

MIXING

The material is supplied ready for use; stir thoroughly with a mechanical paint mixer prior to application.

During mixing and handling of the materials always wear protective goggles, suitable gloves and other protective clothings.

APPLICATION CONDITIONS

Substrate temperature shall be above + 5°C and at least 3°C above the dew point.

Material temperature shall be above + 5°C.

Relative air humidity shall be below 85%.

APPLICATION EQUIPMENT

The following is a guide. Changes in pressures and tip sizes may be needed for satisfactory application characteristics. Always purge spray equipment before use with listed cleaner. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.

Airless Spray

Tip Size: 0.38 – 0.53 mm (0.015 – 0.021 inch)

Fan Angle: 65° - 80°

Operating Pressure: min. 180 bar (2600 psi)

The airless spray details given above are intended as a guide only.

Details such as fluid hose length and diameter, paint temperature and job shape and size all have an effect on the spray tip and operating pressure chosen. However, the operating pressure should be the lowest possible consistent satisfactory atomisation.

As conditions will vary from job to job, it is the applicators responsibility to ensure that the equipment in use has been set up to give the best results.

If in doubt consult Sherwin-Williams customer service.

Conventional Spray

Atomising Pressure: 3 - 5 bar (43 - 72 psi)

Tip Size: 1.7 – 2.5 mm (0.06 – 0.08 inch)

Brush and Roller

Brush and roller application is suitable.

As a good wetting and penetration into the substrate is essential for the efficiency of the priming coat, the best result is achieved by using a distemper brush or similar.



KEM-KROMIK™ 6630 HIGH SOLID / EG

1-PACK SYNTHETIC RESIN COAT

Revised 09/2023 Issue 2

RECOMMENDED SYSTEMS

Steel, blast-cleaned to Sa 2½

1 x Kem-Kromik™ 6630 Primer
1-2 x Kem-Kromik™ 6630 High Solid / EG

Steel, manually prepared

1 x Kem-Kromik™ 6630 Primer or Kem-Kromik™ Aktivprimer Rapid
2 x Kem-Kromik™ 6630 High Solid / EG

Maintenance coating on steel

Touch up with Kem-Kromik™ 6630 Primer or Kem-Kromik™ Aktivprimer Rapid
2 x Kem-Kromik™ 6630 High Solid / EG

Hot-dip galvanized surfaces, stainless steel, copper, aluminium, hard PVC and timber

2 x Kem-Kromik™ 6630 High Solid / EG

ADDITIONAL NOTES

Drying times, curing times and pot life should be considered as a guide only.

Chemical resistance:

Resistance to rural, urban, industrial and marine atmosphere and temporarily exposure to neutral salts.

Not resistant to continuous exposure to diluted acids and alkalis, fatty oils, fuels, mineral oils etc. Temporarily short-term exposure does not harm. Not suitable for continuous exposure to liquids (including water).

Temperature resistance:

Dry heat up to + 80°C.

In case of higher temperatures consult Sherwin-Williams customer service.

Numerical values quoted for physical data may vary slightly from batch to batch.

HEALTH & SAFETY

Consult Product Health and Safety Data Sheet for information on safe storage, handling and application of this product.

WARRANTY

Whilst all statements made about our products (whether in this data sheet or otherwise) are correct and accurate to the best of our knowledge, we have no control over the quality or the condition of the substrate, the application conditions or the many other factors affecting your use and application of our product.

The appropriateness of the product under the actual conditions of application or intended use must be determined exclusively by you. The content of this document, and of any oral or written statements already made or to be made in relation to the subject matter of this document, including any suggestions as to appropriate products and any proposed application methods, technical details and other product information represent only test results or experience obtained under controlled or defined circumstances, and is therefore provided for general information purposes only.

Unless we agree specifically in writing to do so, we will not be liable to you for any loss or damage whether in contract, tort (including negligence), breach of statutory duty, misrepresentation, misstatement or otherwise, arising under or in connection with this document or such statements.

We disclaim any express or implied representations, warranties or guarantees (including any implied warranty of merchantability or fitness for a particular purpose), though nothing in this disclaimer excludes or limits our liability for death or personal injury arising from our negligence, or our fraud or fraudulent misrepresentation, or any other liability that cannot be excluded or limited by law.

All products supplied and technical advice given are subject to our Standard Terms and Conditions of Sale which you should request a copy of and review carefully.

This document may be modified and updated from time to time, and is uncontrolled once printed. It is the users responsibility to ensure they are using the most up to date version – this can be found at: www.sherwin-williams.com/protectiveEMEA.

If this datasheet has been translated, then it has been done using the English version as the source. In case of any queries, please refer to the master English version which can be found at: www.sherwin-williams.com/protectiveEMEA.